

**Nordic Lam™ Scaffold Plank**  
**Nordic Structures**

**PR-L317**

Revised May 31, 2024

Products: Nordic Lam™ Scaffold Plank

Nordic Structures, 1100 Avenue des Canadiens-de-Montréal, Suite 100, Montreal, Québec

Canada H3B 2S2

(514) 871-8526

[www.nordic.ca](http://www.nordic.ca)

1. Basis of the product report:

- ASTM D3737-18e1 (R2023), Standard Practice for Establishing Allowable Properties for Structural Glued Laminated Timber (Glulam)
- ASTM D7341-21, Standard Practice for Establishing Characteristic Values for Flexural Properties of Structural Glued Laminated Timber by Full-Scale Testing
- ANSI A190.1-2022, Product Standard for Structural Glued Laminated Timber
- ANSI/ASSP A10.8-2019, Scaffolding Safety Requirements
- CAN/CSA S269.2-16, Access Scaffolding for Construction Purposes
- CAN/CSA Z797-18, Code of Practice for Access Scaffold
- 2024 AWC NDS<sup>®</sup> Supplement, National Design Specification<sup>®</sup> Design Values for Wood Construction
- APA Reports T2016P-13 and T2017P-10, and other qualification data

2. Product description:

Nordic Lam™ scaffold planks are a Black Spruce structural glued laminated timber (glulam) manufactured in accordance with ES11 and 24F-ES/NPG layup combinations developed in accordance with the principle of ASTM D3737 and ASTM D7341 and documented in APA Product Report PR-L294 ([www.apawood.org/resource-library](http://www.apawood.org/resource-library)). The Nordic Lam scaffold planks are individually proof-loaded in accordance with the in-plant manufacturing standard approved by APA. The Nordic Lam scaffold planks are available in net thickness of 2 inches (ES11) and 1-1/2 inches (24F-ES/NPG), a minimum width of 9 inches, and lengths up to 13 feet (for the maximum application span of 10 feet). Refer to [www.chibou.com](http://www.chibou.com) for application requirements and recommendations.

3. Design properties:

Table 1 lists allowable design values for Nordic Lam scaffold planks published in APA Product Report PR-L294 and confirmed by full-scale scaffold plank tests in accordance with ANSI/ASSP A10.8. Table 2 lists wet service factors, which shall be applied when the average equilibrium moisture content of the planks exceeds 16%. The allowable spans for Nordic Lam scaffold planks are listed in Table 3 for dry use and wet use, based on the OSHA-defined loading. The allowable spans for the CAN/CSA S269.2-defined loading are listed in Table 4 for dry use and wet use. The maximum allowable live load pressures for select spans are presented in Table 5 based on Annex E of CAN/CSA Z797. Selection of Nordic Lam scaffold planks shall be based on the information provided in this report and the recommendations provided by the manufacturer (see link above).

4. Product installation:

Nordic Lam scaffold planks shall be installed in accordance with OSHA ([www.osha.gov](http://www.osha.gov)) or CAN/CSA S269.2 regulations, and the instructions provided by the manufacturer (see link above).

5. Storage, handling, inspection and evaluation:  
 The storage and handling of Nordic Lam scaffold planks shall be in accordance with the recommendations provided by the manufacturer (see link above). Nordic Lam scaffold planks shall be inspected by a qualified person to ensure they are in good condition prior to use. Products showing signs of damage, such as but not limited to splits, dents, gouges, face breaks, discoloration, odor, or decay, shall be removed from service.
  
6. Limitations:
  - a) Nordic Lam scaffold planks shall be designed in accordance with ANSI/ASSP A10.8 or CAN/CSA S269.2 using the design values published in this report.
  - b) Nordic Lam scaffold plank design values published in Table 1 apply to dry service conditions where the average equilibrium plank moisture content is less than 16%. When Nordic Lam scaffold planks are used where the average equilibrium moisture content will be 16% or higher, design values shall be multiplied by the wet service factors specified in Table 2.
  - c) Nordic Lam scaffold planks shall not be used for building components, such as beams or headers.
  - d) Nordic Lam scaffold planks are produced at the Chantiers Chibougamau, Quebec facilities under a quality assurance program audited by APA.
  - e) This report is subject to re-examination in one year.
  
7. Identification:  
 Nordic Lam scaffold planks described in this report are identified by a label bearing the manufacturer's name (Chantiers Chibougamau) and/or trademark, the APA assigned plant number (1057), the product standard (ANSI/ASSP A10.8), the APA logo, the combination symbol, the report number PR-L317, and a means of identifying the date of manufacture.

Table 1. Nordic Lam Scaffold Plank Allowable Design Values <sup>(a, b)</sup>

Layup Combination	ES11	24F-ES/NPG
Plank Bending, $F_{by}$ (psi)	1,750 <sup>(c)</sup>	2,400 <sup>(d)</sup>
Plank Modulus of Elasticity, $E_y$ (psi)	1,500,000	1,800,000
Plank Longitudinal Shear, $F_{vy}$ (psi)	175	300

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.9 kPa.

- <sup>(a)</sup> Allowable design properties are developed based on ASTM D3737, as documented in APA Product Report PR-L294, and confirmed by full-scale scaffold plank tests in accordance with Appendix C of ANSI/ASSP A10.8.
- <sup>(b)</sup> These design values shall not be increased for duration of load and shall apply in dry service conditions where the average equilibrium plank moisture content is less than 16%. When planks are used where the average equilibrium moisture content will be 16% or higher, design values shall be multiplied by the wet service factors specified in Table 2.
- <sup>(c)</sup> The values of  $F_{by}$  are based on members 12 inches in depth. For depths less than 12 inches,  $F_{by}$  shall be permitted to be increased by multiplying by the flat use factor,  $(12/d)^{1/9}$ , where  $d$  is the scaffold plank depth in inches. When  $d$  is less than 3 inches, use the size adjustment factor for 3 inches.
- <sup>(d)</sup> The design value is applicable to scaffold plank products of 1-1/2 inches in thickness.

Table 2. Wet Service Factors,  $C_M$  (for plank moisture content of 16% or higher) <sup>(a)</sup>

Bending ( $F_{by}$ )	Modulus of Elasticity ( $E_y$ )	Longitudinal Shear ( $F_{vy}$ )
0.80	0.833	0.875

<sup>(a)</sup> Based on the Adjustment Factors provided in Table 5C of the NDS Supplement.

Table 3. Allowable Spans for Nordic Lam Scaffold Planks Subjected to OSHA Loading <sup>(a, b)</sup>

OSHA Loading Condition	ES11					24F-ES/NPG				
	2" x 9"	2" x 9 1/4"	2" x 9 1/2"	2" x 11 1/4"	2" x 11 7/8"	1 1/2" x 9"	1 1/2" x 9 1/4"	1 1/2" x 9 1/2"	1 1/2" x 11 1/4"	1 1/2" x 11 7/8"
<b>Simple Span (Feet) – DRY USE ONLY (Less than 16% Moisture Content)</b>										
50 psf	10	10	10	10	10	10	10	10	10	10
75 psf	10	10	10	10	10	8	8	8	8	8
1-Person	10	10	10	10	10	10	10	10	10	10
2-Person	10	10	10	10	10	7	7	8	8	8
3-Person	7	7	7	8	8	5	5	5	6	6
<b>Simple Span (Feet) – WET USE (16% or Higher Moisture Content)</b>										
50 psf	10	10	10	10	10	9	9	9	9	9
75 psf	10	10	10	10	10	8	8	8	8	8
1-Person	10	10	10	10	10	8	8	8	9	10
2-Person	9	9	9	10	10	7	7	7	8	8
3-Person	6	6	6	7	7	4	4	4	5	5

<sup>(a)</sup> Dead load on plank based on glulam density of 42 pcf.

<sup>(b)</sup> Live load deflections are limited to L/60, where L is the allowable span.

Table 4. Allowable Spans for Nordic Lam Scaffold Planks Subjected to CAN/CSA S269.2 Loading <sup>(a, b)</sup>

CAN/CSA S269.2 Loading Condition	ES11					24F-ES/NPG				
	1 1/2" x 9"	2" x 9 1/4"	2" x 9 1/2"	2" x 11 1/4"	2" x 11 7/8"	1 1/2" x 9"	1 1/2" x 9 1/4"	1 1/2" x 9 1/2"	1 1/2" x 11 1/4"	1 1/2" x 11 7/8"
<b>Simple Span (Feet) – DRY USE ONLY (Less than 16% Moisture Content)</b>										
50 psf (2.40 kN/m <sup>2</sup> )	10	10	10	10	10	9	9	9	9	9
75 psf (3.60 kN/m <sup>2</sup> )	10	10	10	10	10	8	8	8	8	8
500 lbf (2.2 kN)	7	8	8	9	9	5	5	5	6	6
Worker & Tools (25 psf + 250 plf) (1.20 kN/m <sup>2</sup> + 3.63 kN/m)	10	10	10	10	10	8	8	8	8	8
Worker & Materials (75 psf + 265 plf) (3.60 kN/m <sup>2</sup> + 3.88 kN/m)	8	8	8	8	8	6	6	6	6	6
<b>Simple Span (Feet) – WET USE (16% or Higher Moisture Content)</b>										
50 psf (2.40 kN/m <sup>2</sup> )	10	10	10	10	10	8	8	8	8	8
75 psf (3.60 kN/m <sup>2</sup> )	9	9	9	9	9	7	7	7	7	7
500 lbf (2.2 kN)	6	6	6	7	8	4	4	4	5	5
Worker & Tools (25 psf + 250 plf) (1.20 kN/m <sup>2</sup> + 3.63 kN/m)	10	10	10	10	10	7	7	7	7	7
Worker & Materials (75 psf + 265 plf) (3.60 kN/m <sup>2</sup> + 3.88 kN/m)	7	7	7	7	7	5	5	5	5	5

<sup>(a)</sup> Dead load on plank based on glulam density of 42 pcf.

<sup>(b)</sup> Live load deflections are limited to L/80, where L is the allowable span.

Table 5. Maximum Uniform Live Loads [psf (kN/m<sup>2</sup>)] for Platforms of Nordic Lam Scaffold Planks Based on Annex E of CAN/CSA Z797 (a, b, c, d)

Layup Combination	Number of layers	Scaffold bay 5 ft (1.52 m) long	Scaffold bay 7 ft (2.13 m) long	Scaffold bay 10 ft (3.05 m) long
ES11	Single	150 (7.2)	150 (7.2)	50 (2.4)
	Double	>150 (>7.2)	>150 (>7.2)	100 (4.8)
	Triple	>150 (>7.2)	>150 (>7.2)	150 (7.2)
24F-ES/NPG	Single	150 (7.2)	75 (3.6)	NR <sup>(e)</sup>
	Double	>150 (>7.2)	150 (7.2)	50 (2.4)
	Triple	>150 (>7.2)	>150 (>7.2)	75 (3.6)

- (a) Dead load on plank based on glulam density of 42 pcf.  
 (b) Live load deflections are limited to L/80, where L is the allowable span.  
 (c) Based on wet stresses.  
 (d) Scaffold platforms are 5-ft (1.52-m) wide.  
 (e) "NR" denotes "not recommended", with allowable live loads of less than 50 psf (2.4 kN/m<sup>2</sup>) at the specified span.

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, Validation Entity, and Product Evaluation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION  
 HEADQUARTERS**

7011 So. 19<sup>th</sup> St. • Tacoma, Washington 98466  
 Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: [www.apawood.org](http://www.apawood.org)

**PRODUCT SUPPORT HELP DESK**  
 (253) 620-7400 • E-mail Address: [help@apawood.org](mailto:help@apawood.org)

**DISCLAIMER**

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. No warranties, express or implied, including as to fitness for a particular purpose, are made regarding this report. Neither APA nor its members shall be liable, or assume any legal liability or responsibility, for damages, direct or indirect, arising from the use, application of, and/or reference to opinions, findings, conclusions or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.